

Product Data Sheet

Edition 01/09/2018

SIMCRETE TILE ADHESIVE - 300 FLOOR TILE ADHESIVE

Ready to use Floor Tile Adhesive for all floor tile laying application.

Product Description

SIMCRETE Dry-Mix Floor Tile Adhesive is a premix high quality adhesive for fixing of all types of tiles such as Ceramic, Vitrified, Porcelain etc for both floor

Comparison with Conventional Mortar

| Parameter | Floor Tile Adhesive | Conventional Method |
|----------------------|--|---|
| Application time | Fast application | Not possible |
| Quality | Consistent quality due to computerized process | Manual mixing, hence not possible to test every batch |
| Shrinkage cracks | Minimum shrinkage cracks | Significantly high shrinkage cracks |
| Handling and storing | Easy handling and storage | Difficult to keep stock of different material |
| Wastage | No wastage | High wastage |
| Efflorescence | Negligible | Observed in many cases |
| Sand | Graded | Not graded |
| Rebound loss | Minimum | High due to non-gradation & bigger sand particle size |

Composition

| No | Chemical Name | Composition |
|----|-------------------------------|-------------|
| 1 | Mortar (Cement & Aggregate) | 91- 93% |
| 2 | Additive 1 | 7% |
| 3 | Polymer | 0.6% |
| 4 | Additive 2 | 0.4% |

Physical & Chemical Properties

| | |
|------------------|----------------------------|
| Apperance | : Grey Powder |
| Odour | : Odorless |
| pH | : 11 - 12.6 |
| Solubility | : Not Applicable |
| Boiling Point | : Not Applicable |
| Melting Point | : Not Applicable |
| Vapour Preassure | : Not Applicable |
| Volatility | : No Information Available |
| Evaporaion rate | : Not Applicable |
| Vapour density | : Not Applicable |
| Specific Gravity | : Not Applicable |
| Flash Point | : No Information Available |
| Flamable limit | : No Information Available |
| Viscosity | : No Information Available |



Form

| | |
|--|---|
| Appearance / Colours | Grey powder |
| Packaging | 20 kg bag |
| Storage | 12 months from date of production if stored properly in original unopened, sealed and undamaged packaging in dry and cool conditions. |
| Storage Conditions / Shelf-Life | 12 months from date of production if stored properly in original unopened, sealed and undamaged packaging in dry and cool conditions. |

Technical Data

| | |
|------------------------|---|
| Chemical Base | Cementitious mortar modified with polymers. |
| Mixed Density | ~ 1.8 to 1.85 gram /cc |
| Layer Thickness | 3- 6 mm |

Mechanical / Physical

Properties

| | | | |
|----------------------------------|---------------------------|-----------------|---------|
| Tensile Adhesion Strength | 1400 N (Dry) 1000 N (Wet) | | |
| Shear Adhesion Strength | 10.2 kN @ 28 days | | |
| Open time | 90 minutes | Pot Life | 225 min |

System Information

Application Details

| | |
|--|--|
| Coverage | 50 - 60 sq.ft/ 20 kg bag) @ 3mm thickness. |
| Substrate Quality | The substrate must be structurally sound, laitance free, clean and free from dirt, oil, grease, other contaminants and loose or friable particles. |
| Substrate Preparation / Priming | Pre-wetting of substrate is essential with maximum saturation of water but saturated surface dry (S.S.D.) condition. |

Application Conditions / Limitations

| | |
|------------------------------|------------------------|
| Substrate Temperature | +5°C min. / +45°C max. |
| Ambient Temperature | +5°C min. / +45°C max. |



Application Instructions

| | |
|--------------------|--|
| Mixing | Water: Powder = 1 : 4 1 p.b.w water for ever 4 p.b.w powder |
| Mixing Time | 3 minutes minimum |
| Mixing Tool | SIMCRET Tile Adhesive - Regular can be mixed on a clean platform or container manually or in a normal grout mixer. Mix thouroughly with clean water for minimum 3 minutes The product is now ready for use |

Application Method

1. The surface of where the adhesive has to be applied should be free from oil, grease, paint, loose plaster and dirt particles. The surface should be rough absorbant to a limited extent, strong and clean.
2. Dampen the surface before application of adhesive for better bonding
3. Water should be taken 1 : 4 ratio , i.e, for ever 1 part by weight water, 4 part by weight powder
4. Leave the mixture to react for 5 minutes.
5. For better coverage use notched trolvel to spread the adhesive

| | |
|--------------------------|---|
| Cleaning of Tools | Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be removed mechanically. |
|--------------------------|---|

Hazard Identification

According to the present state of knowledge, this product is safe for handling and has no adverse effect to humans or environment

First Aid Measures

| | |
|--------------|---|
| Eye Contact | : Avoid falling into the eyes. Rinse the eye with plenty of water, at the same time keep the unaffected eye well protected. |
| Inhalation | : Remove the casualty into fresh air. If the problem persists such as cough or throat irritation. Seek medical help |
| Skin contact | : Wash thouroughly the affected area with running water. |
| Ingestion | : Do not induce vomiting. Keep individual calm and seek medical assistance. |



Fire Protection Measures

| | |
|---------------------------|---|
| Fire | : Not considered a fire hazard material |
| Explosion | : Not considered a explosive material. |
| Fire extinguishing media | : Use agent appropriate to extinguish surrounding fire such as water spray, powder or foam. |
| Fire fighting instruction | : In the event of a fire, wear full protective clothing with face shield. |

Accidental Release Measures

| | |
|-----------------------------|--|
| General Protective Measures | : Use proper personal protective equipment as indicated. |
| Cleanup Procedure | : Scoop or sweep up spilled material and place into suitable container for disposal, Flush with water. |

Handling & Storage

| | |
|----------|--|
| Handling | : Wear protective garments, helmets, eyewear during handling, avoid contact with eyes. |
| Storage | : Store in warm, ventilated & dry places. |

Exposure Control & Personal Protection

| | |
|--------------------------|---|
| Airborne Exposure Limits | : ACGIH TWA 10 mg/m ³ (Nuisance Dust) |
| Ventilation System | : All system of local or general exhaust is recommended to keep workers exposure as low as possible |
| skin protection | : Wear appropriate protective clothing, including boots, gloves, coveralls to minimise contact with skin |
| Eye Protection | : Use chemical safety goggles or face shield wherever splashing is possible. Maintain eye wash and quick drench facilities in work place. |

Stability & Reactivity

| | |
|----------------------------------|--|
| Stability | : Stable under ordinary conditions of use and storage. |
| Hazardous Decomposition products | : Potential irritating & toxic gases may be generated by thermal decomposition |
| Hazardous Polymerization | : Not Known |
| Conditions to avoid | : Incompatible materials, dust generation, acid and excess heat. |



Toxicological Information

| | |
|-------------------------|----------------------------|
| Toxicity area | : No information available |
| Carcinogenicity | : No information available |
| Reproductive effect | : No information available |
| Effects of overpressure | : No information available |
| Chronic effects | : No information available |
| Target organs | : No information available |

Toxicological Information

Adverse ecological effects in the use of this product is not known.

Disposal Information

What ever material that cannot be saved , recovered or recycleable should be moved away to approved waste facility. Spend material or off specification material in significant quantity and in paste form should not be disposed off in sewage or sanitary land fills unless effectively treated. If there is any doubt as to the methods of disposal it should refered to the Department of Environmen.

Transport Information

The material should be transported in sealed condition in suitabls bags and pallets.

Regulatory Information

Not available

Notes on Application / Limitations

Cementitious substrates must be at least 28 days old.

Do not exceed the recommended water dosage. Apply only to sound, prepared substrates. Do not exceed the maximum layer thickness.

Protect freshly applied material from freezing and rain etc.

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.



Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of SIMCRETE products are given in good faith based on SIMCRETES knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with SIMCRETE'S recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. SIMCRETE reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

